



FEATURES

- ▶ 7 x 7 mm to 28 x 28 mm body size with 1.4 mm body thickness
- ▶ 32-256 lead counts
- ▶ Pre-plated frame options
- ▶ Inverted pad configuration
- ▶ Cu, Ag and Au wire available
- ▶ Large selection of die pad sizes and custom leadframe design available
- ▶ Optimal for stacked die
- ▶ Pb-free RoHS compliant materials

APPLICATIONS

Amkor's LQFPs are an ideal package for most IC semiconductor technologies such as ASIC, PMU controllers, microprocessors, gate arrays (FPGA/PLD) and PC chip sets.

LQFP packages are particularly well suited for electronic systems requiring broad performance characteristics. Such applications include laptop PCs, video/audio, telecom, RF, data acquisition, set-top box, communication boards and automotive.



LQFP

Amkor offers a broad line of LQFP (Low-profile Quad Flat Package) IC packages designed to provide the same great benefits as TQFP packaging with a 1.4 mm body thickness. These packages allow IC packaging engineers, component specifiers and systems designers to solve issues such as increasing board density, die shrink programs and thin end-product profile.

Thermal Performance

Single-Layer PCB

Package	Body Size (mm)	Pad Size (mm)	θ_{JA} at ($^{\circ}\text{C/W}$) by Velocity (LFPM)		
			0	200	500
32 Ld	7 x 7	5 x 5	67.8	55.9	50.1
100 Ld	14 x 14	8 x 8	41.5	33.4	29.5
144 Ld	20 x 20	8.5 x 8.5	38.0	31.2	28.1
176 Ld	24 x 24	8 x 8	38.3	31.9	29.0

JEDEC standard test boards

Multi-Layer PCB

Package	Body Size (mm)	Pad Size (mm)	θ_{JA} at ($^{\circ}\text{C/W}$) by Velocity (LFPM)		
			0	200	500
32 Ld	7 x 7	5 x 5	47.9	42.1	39.4
100 Ld	14 x 14	8 x 8	31.7	26.8	24.7
144 Ld	20 x 20	8.5 x 8.5	31.7	26.9	24.9
176 Ld	24 x 24	8 x 8	31.9	27.3	25.4
208 Ld*	28 x 28	16 x 16	18.1	15.3	14.4

JEDEC standard test boards

*Pre-JEDEC standard test boards, tested @ 1W

Electrical Performance

Simulated Results @ 100 MHz

Package	Body Size (mm)	Pad Size (mm)	Lead	Inductance (nH)	Capacitance (pF)	Resistance (m Ω)
32 Ld	7 x 7	5 x 5	Longest Shortest	0.904 0.799	0.211 0.202	9.2 7.8
48 Ld	7 x 7	5 x 5	Longest Shortest	1.110 0.962	0.225 0.200	13.8 12.0
100 Ld	14 x 14	8 x 8	Longest Shortest	2.300 1.520	0.419 0.322	26.3 17.8
144 Ld	20 x 20	8.5 x 8.5	Longest Shortest	6.430 4.230	1.100 1.070	62.9 52.6
176 Ld	24 x 24	8 x 8	Longest Shortest	9.510 5.200	1.270 1.340	89.0 64.0
208 Ld	28 x 28	11 x 11	Longest Shortest	9.670 6.190	1.380 1.210	86.2 64.8

LQFP

Reliability Qualification

Amkor devices are assembled in optimized package designs with proven reliable semiconductor materials.

Commercial Reliability Levels

- ▶ Moisture sensitivity characterization: JEDEC level 3, 30°C/60% RH, 192 hours
- ▶ Temp cycle "C": -65°C/+150°C, 500 cycles
- ▶ uHAST: 130°C/85% RH, 96 hours
- ▶ High temp storage: 150°C, 1000 hours
- ▶ AEC-Q100 qualified

Process Highlights

- ▶ Die thickness: 14.5 ± .5 mil
- ▶ Strip solder plating: Matte Sn, pre-plated Ni/Pd frames, roughened Cu leadframe option
- ▶ Marking: Laser
- ▶ Lead inspection: Laser/optical
- ▶ Pack/Ship options: Barcode, dry pack
- ▶ Wafer backgrinding available


Test Services

- ▶ Program generation/conversion
- ▶ Product engineering support
- ▶ Wafer sort
- ▶ -55°C to +165° test available

Shipping

- ▶ JEDEC outline CO-124 low-profile tray
- ▶ Tape and reel

Cross Section LQFP



Configuration Options

LQFP Nominal Package Dimensions (mm)

Lead Count	Body Size	Body Thickness	Lead Form	Standoff	Foot Length	Tip-to-Tip	JEDEC	Tray Matrix	Units Per Tray
32/48/64	7 x 7	1.40	1.00	0.10	0.60	9.0	MS-026	10 x 25	250
44/52/64/80	10 x 10	1.40	1.00	0.10	0.60	12.0	MS-026	8 x 20	160
80	12 x 12	1.40	1.00	0.10	0.60	14.0	MS-026	7 x 17	119
64/80/100/120/128	14 x 14	1.40	1.00	0.10	0.60	16.0	MS-026	6 x 15	90
128/144/176	20 x 20	1.40	1.00	0.10	0.60	22.0	MS-026	5 x 12	60
160/176/216	24 x 24	1.40	1.00	0.10	0.60	26.0	MS-026	4 x 10	40
280/256	28 x 28	1.40	1.00	0.10	0.60	30.0	MS-026	4 x 9	36



Visit amkor.com or email sales@amkor.com for more information.

With respect to the information in this document, Amkor makes no guarantee or warranty of its accuracy or that the use of such information will not infringe upon the intellectual rights of third parties. Amkor shall not be responsible for any loss or damage of whatever nature resulting from the use of, or reliance upon it and no patent or other license is implied hereby. This document does not in any way extend or modify Amkor's warranty on any product beyond that set forth in its standard terms and conditions of sale. Amkor reserves the right to make changes in its product and specifications at any time and without notice. The Amkor name and logo are registered trademarks of Amkor Technology, Inc. All other trademarks mentioned are property of their respective companies. © 2019 Amkor Technology, Incorporated. All Rights Reserved. DS232G-EN Rev Date: 07/19

